



Northern Forest Products

Species Weights
Kiln Dried Weight per Board Foot



Species	Rough	H/M	13/16"
Alder	2.3	2.2	1.9
Ash	3.4	3.2	2.8
Aspen	2.2	2.1	1.8
Basswood	2.1	2.0	1.7
Domestic Beech	3.6	3.4	2.9
Paper White Birch	3.1	2.9	2.5
Yellow Birch	3.5	3.3	2.9
Butternut	2.2	2.1	1.8
Aromatic Red Cedar	2.6	2.5	2.1
Cherry	2.9	2.7	2.4
Cypress	2.6	2.4	2.1
Hickory	4.1	3.9	3.4
Hard Maple	3.5	3.3	2.9
Soft Maple	3.0	2.8	2.5
Red Oak	3.6	3.4	2.9
White Oak	3.8	3.6	3.1
Pine, White	2.1	2.0	1.7
Poplar	2.5	2.3	2.0
Walnut	3.2	3.0	2.6
Anigre	4.3	4.0	3.5
European Beech	3.8	3.5	3.0
Bubinga	4.4	4.1	3.6
Jatoba	4.7	4.4	3.8
Lyptus	4.4	4.1	3.6
African Mahogany	2.5	2.3	2.0
Honduras Mahogany	2.7	2.5	2.2
Makore	3.3	3.0	2.6
Padouk	4.4	4.1	3.6
Purpleheart	4.0	3.8	3.3
Sapele	3.4	3.2	2.8
Teak	3.2	3.0	2.6
Zebrawood	3.6	3.4	2.9



Northern Forest Products
2050 Main Street
Centerville, MN 55038
651-429-9990
651-429-9993 fax